Ovuli10FL SS-ALP

Product code: OVC10 SS-ALP

Flange OVC10 SS-ALP_F

or double pole arm installation.

grooved column (SS) and capital (ALP).



Cast iron pole with steel core and cast iron base, prepared for single

The pole is equipped with an M12 screw, steel inox AISI 304 (grounding).

The pole is composed of: base with decorative element, double

ALP 763 mm

SS 820 mm

4.640 mm



cast-iron | data sheet: 2020.03

01 | 02

Conformity

CE EN40-5

Geometry and mechanical features

Total height: Total weight: 4.640 mm () flange: 99 Kg () foundation: 101 Kg

Materials Color Base:

Column | Capital: Core: Color: Cast-iron | EN1561 Cast-iron | EN1561 Steel S235 - hot galvanized | UNI EN 10219 - EN1461 Dark grey (ferromicaceo) Ghisamestieri®


Base Ovuli10FL

Ø 60

Scale: 1:15

30 Kg






Pole arms Standard




Fixing type

() Flange



Foundation



Supplied: Heat-shrink sheath

290 mm Scale: 1:25

GMR ENLIGHTS s.r.l. • Quality system certificate ISO 9001:2015-ISO 14001:2015 • phone:+39-0543-462611 • fax:+39-0543-449111 • info@gmrenlights.com • www.gmrenlights.com We reserve the right to make improvements or changes at any time without prior notice. The pictures used are purely for information. Dimensional tolerance +/- 1% • weight tolerance +/- 3%.

Ø 102

G. L.

Protection cycles

GMR ENLIGHTS

2020.03 02 02

GMR ENLIGHTS works with cast iron, steel and aluminum. The materials are selected and processed to maximize performance and quality.

Protection of galvanized steel surfaces for poles

CAST IRON

DIE-CAST ALUMINIUM

The protection of galvanized steel elements is achieved by following steps:

 Micro sandblasting; • First epoxy layer application followed by: Wilting > Drying > Cooling; • Acrylic glaze layer application followed by: Wilting > Drying > Cooling; • Packing at least after 24-hour-drying at room temperature.

Protection of galvanized steel surfaces for brackets and pastorals

The protection of the galvanized steel elements is achieved thanks to:

- Micro sandblasting;
- Phosphoric pickling bath at a ph level ranging from 1.5 to 3;
- Rinsing with demineralised water;
- First powder layer application;
- Kiln firing;
- Application of a final powder layer;
- Kiln roasting of the final powder layer at 180°;
- Cooling.

Protection of cast iron surfaces for bases

The protection of cast iron elements is achieved by the following

- Surface micro shotblasting;
- Mono-component dip galvanizing followed by:
- Wilting > Drying > Cooling;

- Acrylic enamel application followed by:
- Wilting > Drying > Cooling;

Protection of die-cast aluminium surfaces for lighting fixtures, tops, collars, brackets and pastorals

Brackets, pastoral, and die-cast accessories undergo a cycle of powder painting which creates a barrier against the corrosion of metal parts. Moreover this barrier makes the finished product comply with design specifications in terms of surface roughness, color and reflectance. The cycle consists of the following steps:

- Micro sandblasting;
- Hot pickling bath in a zinc-based phosphodegreasing solution;
- · Specific process for the preparation of surfaces before painting;
- Washing with water;
- Rinsing with demineralised water and subsequent drying;
- First bowder layer application followed by kiln baking at 180°;
- Final powder layer application using a High Durability product and final kiln roasting at 180°C.



Salt spray test | FLORIDA TEST

The top quality of such treatments is confirmed by salt spray tests performed in accordance with standard ISO 9227:2017 Neutral Salt Spray test (NSS). The test was carried out for 8.000 hours at 35 °C and demostrated through the report test released.



GMR ENLIGHTS s.r.l

Legal headquarters: Strada Provinciale Specchia - Alessano, 68 • 73040 (LE)

> Administrative and operational headquarters: Via Grande n°226 • 47032 Bertinoro (FC)

> > T+39 0543 462611 F+39 0543 449111

info@gmrenlights.com www.gmrenlights.com

treatments:

- Epoxy micaceous primer application followed by:
- Wilting > Drying > Cooling;

• Packing at least after 24-hour-drying at room temperature.