
Trali large pole arm



rev. 2020.06

Product code: TRM L



Pole arm predisposed for the installation of suspended lighting fixtures. Available in single, double, triple or quad versions on 7-8-9-10 m. poles. The pole arm is equipped for the pole fixing and for the suspended lighting fixtures fixing.

CONFORMITY

CE EN40-5

GEOMETRY AND MECHANICAL FEATURES (*)

Height:	629 mm
Widht: Weight:	1245 mm (pole collar excluded) 5,6 Kg (pole collar excluded)
Extension:	1250 mm
(*): Referred to single version	

MATERIALS | COLOR

Mensola (A): Tappo di chiusura (B): Attacco collare a palo (C1): Collare a palo (C2): Collare attacco tirante (C3): Elemento decorativo (D): Tirante (E) **Bulloneria:**

Acciaio S355 | EN 10083-1 Materiale plastico Acciaio C30 | EN 10083-1 Acciaio C40 | EN 10083-1 Acciaio C30 | EN 10083-1 Pressofusione di alluminio | EN 1706 Acciaio Inox AISI 304 Acciaio Inox AISI 304

POLE COLLARS (C2)

Grigio scuro Scale: 1:10



Lighting fixture fixing system



Fast connection

An axle box is welded to the pole arm (A) to allow the fast connection of the Ghisamestieri lighting fixture (X). A die-cast aluminium decoration (D) hide the fixing system.



GMR ENLIGHTS s.r.l. • Quality system certificate ISO 9001:2015-ISO 14001:2015 • phone:+39 0543 462611 • fax:+39 0543 449111 • info@gmrenlights.com • www.gmrenlights.com The information in the data sheet may be subject to variations and implementations; please check the latest news on www.gmrenlights.com

Protection cycles

GMR ENLIGHTS

GMR ENLIGHTS works with cast iron, steel and aluminum. The materials are selected and processed to maximize performance and quality.

Protection of galvanized steel surfaces for poles

The protection of galvanized steel elements is achieved by following steps:

 Micro sandblasting; • First epoxy layer application followed by: Wilting > Drying > Cooling; • Acrylic glaze layer application followed by: Wilting > Drying > Cooling; • Packing at least after 24-hour-drying at room temperature.

Protection of galvanized steel surfaces for brackets and pastorals

The protection of the galvanized steel elements is achieved thanks to:

- Micro sandblasting;
- Phosphoric pickling bath at a ph level ranging from 1.5 to 3;
- Rinsing with demineralised water;
- First powder layer application;
- Kiln firing;
- Application of a final powder layer;
- Kiln roasting of the final powder layer at 180°;
- Cooling.

Protection of cast iron surfaces for bases

The protection of cast iron elements is achieved by the following treatments:

- Surface micro shotblasting;
- Mono-component dip galvanizing followed by:
- Wilting > Drying > Cooling;
- Epoxy micaceous primer application followed by:
- Wilting > Drying > Cooling;
- Acrylic enamel application followed by:

Protection of die-cast aluminium surfaces for lighting fixtures, tops, collars, brackets and pastorals

Lighting fixtures, brackets, pastoral, and die-cast accessories undergo a cycle of powder painting which creates a barrier against the corrosion of metal parts. Moreover this barrier makes the finished product comply with design specifications in terms of surface roughness, color and reflectance.

The cycle consists of the following steps:

- Micro sandblasting;
- · Hot pickling bath in a zinc-based phosphodegreasing solution;
- Specific process for the preparation of surfaces before painting;
- Washing with water;
- Rinsing with demineralised water and subsequent drying;
- First bowder layer application followed by kiln baking at 180°;
- Final powder layer application using a High Durability product and final kiln roasting at 180°C.



Salt spray test

The top quality of such treatments is confirmed by salt spray tests performed in accordance with standard ISO 9227:2017 Neutral Salt Spray test (NSS). The test was carried out for 8.000 hours at 35°C and demostrated through the report test released.



GMR ENLIGHTS s.r.l

Legal headquarters: Strada Provinciale Specchia - Alessano, 68 • 73040 (LE)

> Administrative and operational headquarters: Via Grande n°226 • 47032 Bertinoro (FC)

> > T+39 0543 462611 F+39 0543 449111

info@gmrenlights.com www.gmrenlights.com

- Wilting > Drying > Cooling;
- Packing at least after 24-hour-drying at room temperature.

The information in the data sheet may be subject to variations and implementations; please check the latest news on www.gmrenlights.com



DIE-CAST ALUMINIUM

CAST IRON