Vesta Klepsi 035

Product code: VKP035

Flange VKP035_F

lighting fixture Vesta C.





Geometry and mechanical features

3.560 mm

① flange: 31 Kg T foundation: 32 Kg




2020.10 01 | 02




Total height:

Total weight:



The pole is equipped with M12 screw, AISI 304 stainless steel (grounding).



Scale: 1:20

GMR ENLIGHTS s.r.l. • Quality system certificate ISO 9001: 2015 - ISO14001:2015 • phone +39 0543 462611 • fax. +39 0543 449111 • sales@gmrenlights.com • www.gmrenlights.com The information in the data sheet may be subject to variations and implementations; please check the latest news on www.gmrenlights.com • The values have a tolerance of +/- 5%.



2020.10

02 | 02

Protection cycles

Protection of galvanized steel surfaces for poles

The protection of galvanized steel elements is achieved by following steps:

Micro sandblasting
First epoxy layer application followed by: Wilting > Drying > Cooling
Acrylic glaze layer application followed by: Wilting > Drying > Cooling
Packing at least after 24-hour-drying at room temperature.

Protection of galvanized steel surfaces for brackets and pastorals

The protection of the galvanized steel elements is achieved thanks to:

- Micro sandblasting
- Phosphoric pickling bath at a ph level ranging from 1.5 to 3
- Rinsing with demineralised water
- First powder layer application
- Kiln firing
- Application of a final powder layer
- Kiln roasting of the final powder layer at 180°
- Cooling.

Protection of cast iron surfaces for bases

The protection of cast iron elements is achieved by the following treatments:

- Surface micro shotblasting
- Mono-component dip galvanizing followed by:
- Wilting > Drying > Cooling
- Epoxy micaceous primer application followed by:
- Wilting > Drying > Cooling
- Acrylic enamel application followed by: Wilting > Drying > Cooling.
- Packing at least after 24-hour-drying at room temperature.

Protection of die-cast aluminium surfaces for lighting fixtures, tops, collars, brackets and pastorals

Brackets, pastoral, and die-cast accessories undergo a cycle of powder painting which creates a barrier against the corrosion of metal parts. Moreover this barrier makes the finished product comply with design specifications in terms of surface roughness, color and reflectance. The cycle consists of the following steps:

- Micro sandblasting
- Hot pickling bath in a zinc-based phosphodegreasing solution
- Phospho-chromatation for surfeces clearing
- Washing with water
- Rinsing with demineralised water and subsequent drying
- First bowder layer application followed by kiln baking at 180°
- Final powder layer application using a High Durability product and final kiln roasting at 180°C.



Salt spray test | FLORIDA TEST

The top quality of such treatments is confirmed by the succesfull results of specific salt spray test (all products exceed widely 2.500 hours) and the strictest international tests, among which FLORIDA TEST. The salt spray test is made in accordance with standard UNI EN ISO 9227.



GMR ENLIGHTS s.r.l

Legal headquarters: Strada Provinciale Specchia - Alessano, 68 • 73040 (LE)

> Administrative and operational headquarters: Via Grande n°226 • 47032 Bertinoro (FC)

> > T +39 0543 462611 F +39 0543 449111

sales@gmrenlights.com www.gmrenlights.com